

# Whiteboard PP Dryapply ASLAN WBL 998



PVC free whiteboard film for easy dry applications even in large formats

The self-adhesive whiteboard film turns every surface into a writable whiteboard. The scratch resistant surface ensures that writings can be wiped off dry without leaving any shadows or ghostings. Finest air release channels allow air bubbles to be wiped out with ease and make the application of the PVC free self-adhesive film fast and easy.

For additional information please contact our technical advisory service:  
**+49 (0) 22 04. 7 08-80**

## Construction

face-film:	PP with special laquering	
thickness:	~ 150 µm	
adhesive:	polyacrylate adhesive	square quantity: ~ 25 g/m <sup>2</sup>
release liner:	embossed silicone paper, PE-coated on both sides	square weight: ~ 130 g/m <sup>2</sup>

## Characteristics

adhesive strength: (ASTMD-903)	immediately after 72 hours	~ 6 N/25 mm ~ 12 N/25 mm
dimensional stability:	applied onto aluminum after 48 hours stored at 70 °C (25 x 25 cm)	no shrinkage measurable
chemical resistance:	In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and aliphatic solvents, mild acids, alkalis and salts.	
temperature:	application temperature: service temperature range:	min. 15°C -30 °C up to +80 °C
minimum durability:	2 years outdoors, with vertical exposure, in central-European climate.	

**ASLAN, Schwarz GmbH & Co. KG**  
Oberauel 2 · 51491 Overath · Germany  
**phone** +49 (0) 2204. 708 80 · **fax** +49 (0) 2204. 708 50  
**e-mail** info@ASLAN-Schwarz.com



[www.ASLAN-Schwarz.com](http://www.ASLAN-Schwarz.com)

**ASLAN**   
EXPERTISE IN SELF-ADHESIVE FILMS

# Whiteboard PP Dryapply ASLAN WBL 998

**Dry  
apply**

## Processing

application:

Dry application only.

**Important**

We do not recommend a large-scaled application of whiteboard films with mounting tapes. The writable surface of the film can be damaged by taking off the tape so removability cannot be guaranteed anymore. If it is nevertheless necessary using a mounting tape we recommend a tape with low adhesion. The tape should be taken off from the middle of the material to the edge.

The substrate must be free of dust, grease and oil.

cleaning:

Writing with whiteboard markers can be easily wiped off dryly using a microfibre cloth, without leaving any ghosting and shadows. If you used by mistake inappropriate pens, i.e. a permanent marker, you can clean the films with alcohol or white gas for cleaning purposes without leaving any residues.

storage life:

Before application the films can be stored for minimum 2 years from date of production. The film must be stored at room temperature (15-25 °C) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

State: 03 | 2019

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

**ASLAN, Schwarz GmbH & Co. KG**

Oberauel 2 · 51491 Overath · Germany

**phone** +49 (0) 2204.708 80 · **fax** +49 (0) 2204.708 50

**e-mail** info@ASLAN-Schwarz.com



[www.ASLAN-Schwarz.com](http://www.ASLAN-Schwarz.com)

**ASLAN**®

EXPERTISE IN SELF-ADHESIVE FILMS