



MUG I65

With a highly specific multi alloy metal composition, the MUG I65 film constitutes a significant barrier to solar absorption. It is highly effective in shielding against solar heat gain and further protects glazed surfaces from damage.



Warranty

10 YEARS



Fire-resistance rating

M1



Storage from -5°C to +40°C

3 YEARS



REACH RoHS compliant

RESPECTED



EN 61000-5-7

RESPECTED



ASTM D4935-18

RESPECTED

WIDTHS AVAILABLE:

↔ **122 cm**

↔ **152 cm**


TECHNICAL DATASHEET

Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	47 %
Reflection of external visible light	29 %
Reflection of internal visible light	28 %
Total solar energy rejected	66 %
Total solar energy rejected 2*	63 %
Solar ratio :	
Solar energy reflection	47 %
Solar energy absorption	25 %
Solar energy transmission	28 %
Reduction in Solar Glare	52 %
g-value	0.36
u-value	4.9
Heat loss Reduction (Winter)	
Rejected Infrared (760-2500 nm)	+/- 80 %
Shading coefficient	0.4
Installation type : Internal application	
Roll length	30,5 m
PET / PVC composition	PET
Thickness	55 µ
Colour : CHAMPAGNE	

CONSTRUCTION

1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
2. High optical quality polyester, with anti IR metal particles deposit
3. Bonding adhesive
4. High optical quality polyester
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation



MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 0805 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film. To prevent a possible oxidation of the metal alloys, it is mandatory to use our sealing varnish (reference number 0771) on the corners of the film, after installation.

Non-contractual data. We reserve the right to modify the composition of our films at any time. Consult our warranty documents.

INSTALLATION ADVICE

Vertical installation and on standard glass surface**

Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	✓
Reflective tinted double pane	✓
Gas-filled double pane - Low E	✓
STADIP EXT. clear double pane	✓
STADIP INT. clear double pane	!

✓ Yes ! Caution ✗ Not recommended

*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.