



COMMERCIAL TESTING COMPANY

1215 South Hamilton Street • Dalton, Georgia 30720
 Telephone (706) 278-3935 • Facsimile (706) 278-3936

Report Number 16-10316

HP, Inc.
 San Diego, California

Test Number 4545-1503-1016RR2
 June 13, 2014

ASTM F793

Test Method: The material was tested in accordance with ASTM International standard classification F793-10a, *Wall Covering by Use Characteristics*, which covers the classification of wall covering according to its serviceability in use.

Material Tested: The client submitted a sample of fabric backed wall covering identified as **HP PVC-free Durable Wall Paper Printed with HP Latex 200 Printer series / HP L26500 with HP 792 Latex Inks.**

Characteristic	Category V Type II Requirement	Test Data	Test Result
Colorfastness to Light	≥ 200 h	200 hours	Pass
Washability	≥ 100	100 cycles	Pass
Scrubability	≥ 300	300 cycles	Pass
Abrasion Resistance	≥ 300	300 cycles	Pass
Breaking Strength, Machine Direction	≥ 50 lbf	144 lbf	Pass
Breaking Strength, Cross Machine	≥ 55 lbf	112 lbf	Pass
Crocking, Dry	Good	Excellent	Pass
Stain Resistance to Reagents	1-12	(See Note)	Pass
Tear Resistance, Machine Direction	≥ 400 gf	1075 gf	Pass
Tear Resistance, Cross Machine	≥ 400 gf	826 gf	Pass
Blocking Resistance	≤ 2	1	Pass
Coating Adhesion (MD), lbs/inch	≥ 3	3.2	Pass
Coating Adhesion (CMD), lbs/inch	≥ 3	3.8	Pass
Cold Crack Resistance	No Change	No Change	Pass
Heat Aging Resistance	Pass	Pass	Pass
Shrinkage, Machine Direction	≤ 2%	0.124%	Pass
Shrinkage, Cross Machine Direction	≤ 1%	-0.132%	Pass

Note — Stain Resistance

Reagent	Rating	Reagent	Rating
(1) 75°F distilled water	5	(7) standard soap solution	4.5
(2) 120°F distilled water	4.5	(8) detergent solution	4.5
(3) 50% ethyl alcohol	5	(9) orange juice	5
(4) vinegar	4	(10) butter	5
(5) 1% NaOH solution	4	(11) catsup	5
(6) 5% HCl	4	(12) tea	4.5

Note: The rating system is based on the AATCC *Nomenclature for Subjective Rating Processes* in which a rating of 5 = negligible or no staining, 4 = slight staining, 3 = noticeable staining, 2 = considerable staining, and 1 = severe staining. A rating of less than 4 is considered "appreciable" in relation to severity of change.

Commercial Testing Company

(Authorized Signature)

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. The test results presented in this report apply only to the samples tested and are not necessarily indicative of apparent identical or similar materials. Sample selection and identification were provided by the client. A sampling plan, if described in the referenced standard, was not necessarily followed. This report, or the name of Commercial Testing Company, shall not be used under any circumstance in advertising to the general public.