



Test Report

Determination of friction

Report-No.: 903 6998-2/Sgm

Client: Avery Dennison Materials Belgium sprl.
Bld Kennedy, Z.I. Zone B
7060, Soignies, Belgium

Order-No. (Client): -

Order-No. (MPA): 903 6998 000

Test Item: JT 8300 WM-RT DOT Floor Printed – UV inks

Specification Applied: [1] DIN EN 13036-4: 2011-12
Road and airfield surface characteristics – Test methods –
Part 4: Method for measurement of slip/skid resistance of a
surface – The pendulum test

Date of Receipt of Test Item 13.05.2019

Date of Test: 15.05.2019

Date of Report: 16.05.2019

Page 1 of 2 text pages

Enclosures : -

Supplements: -

Total Number of Pages: 2

Number of Reports: 1

The test results relate only to the items tested.

Publication of this report in full or partly is only allowed with written authorization by MPA University of Stuttgart.

1 Purpose of Investigation

You commissioned us with testing of friction properties of the sample “**JT 8300 WM-RT DOT Floor Printed – UV inks**” according to DIN EN 13036-4 [1] (dry conditions). For testing the samples were fixed on a piece of parquet.

2 Testing procedure

The test was performed according to DIN EN 13036-4 [1] (accredited test according to DIN EN ISO/IEC 17025, see DAkkS-certificate D-PL-11027-04-07).


3 Results of Investigation

The following test results were obtained.

Table 1: Test results, friction of “**JT 8300 WM-RT DOT Floor Printed – UV inks**” on parquet according to DIN EN 13036-4 [1] (dry conditions)

testing spot no.	Friction (PTV-value)	
	longitudinal direction (dry condition)	transverse direction (dry condition)
1	89	92
2	89	93
3	88	92
4	87	92
5	88	93
Average	88	92


Prepared by



Oliver Konrad
Testing Engineer



Approved and released by



Dr.-Ing. Michael Stegmaier
Section leader

The test results relate only to the items tested.

Publication of this report in full or partly is only allowed with written authorization by MPA University of Stuttgart.